

DIFFERENTIAL THERMAL ANALYSIS OF CLAYS AND CARBONATES *

BY RICHARDS A. ROWLAND **

ABSTRACT

Differential thermal analysis (DTA) began soon after the development of the thermocouple. It has progressed through the systematic development of better equipment and the cataloguing of typical DTA curves for a variety of materials until good technique now requires control of the composition and pressure of the furnace atmosphere as well as consideration of the thermodynamics and kinetics of the reactions involved. Although differential thermal analyses have been made for many materials, the major applications have been concerned with clay and carbonate minerals.

In DTA curves for clay minerals the low-temperature endothermic loop associated with the loss of water, and the high-temperature exothermic loop accompanying the formation of new compounds, are changed in shape, temperature, and intensity by the kind of exchange cations. The midtemperature-range endothermic loop has a temperature dependence on the partial pressure of water in the furnace atmosphere.

For the anhydrous normal carbonates the dissociation temperature and its dependence on the partial pressure of CO₂ are in the decreasing order Ca, Mg, Mn, Fe, and Zn. The lower temperature loop of dolomite, the reaction for which must be preceded by an internal rearrangement, is independent of the pressure of CO₂ but may be shifted to a lower temperature by prolonged fine grinding which accomplishes a similar rearrangement.

INTRODUCTION

Differential thermal analysis (DTA), although not a very accurate or definitive method, has found an important place among techniques which allow the characterization of materials. Limited only by the sensitivity of the apparatus, the differential thermal curves record all transformations in which heat is taken up or given off. This includes the dehydration of clays, the decarbonation of carbonates, the reversible change from α - to β -quartz, the burning of materials, and the recombination of elements into more stable forms. When employed alone, the technique can be used to identify a number of reasonably pure compounds and to follow changes in mixtures for control purposes. When used in conjunction with X-ray diffraction, microscopy, and chemical analysis, otherwise difficult identifications can be made. The technique is not easily standardized, however, and the factors which frequently make it difficult to compare DTA curves prepared in different laboratories are summarized by Ahrens (1950).

The development of differential thermal analysis has progressed through several stages. As early as 1887 le Chatelier described the use of his thermocouple as a difference thermocouple and published DTA curves of kaolinite. From that time until Orzel (1935) began the systematic differential thermal analyses of clays, about twenty miscellaneous DTA papers appeared. Another stage began with the design of good furnaces, sample holders, and photographic recording equipment by Norton (1939) and Hendricks (1939). Refinements of this design by Grim and Rowland (1942) were followed by further developments by Berkelhamer and Spiel (1944). Throughout this period many papers appeared which repeated the thermal curves of the same clay samples and related oxides, and a portable apparatus

was developed by Hendricks (1946)¹ for use in studying bauxite deposits in the field. The last development in the basic apparatus was the visual recording of the DTA curves of a number of samples being heated in the same furnace. Simultaneous development of DTA techniques for the elementary study of carbonate minerals took place in the U. S. A., Japan, and the U. S. S. R.

Reconsideration of the thermodynamics of the system gave rise to a very sensitive sample holder (Gruver, 1948) (Kaufman and Dilling, 1950) made of platinum foil. Herold (1948) developed a thin sample holder half platinum and half platinum-10 percent rhodium in which the thermocouple junction, built into the sample holder, was a ring around the middle of the cylindrical sample. Development of static atmosphere control within the furnace was introduced by Saunders and Giedroye (1950) and Rowland and Lewis (1951). Dynamic atmosphere control within the sample was introduced by Stone (1952)² Presently the trend is toward atmosphere control at elevated pressures where DTA reactions begin to approach equilibrium reactions. From the simple approximate measurement of the effective temperature difference obtained by comparing the temperature of the reaction of a sample in its own atmosphere with that of an inert standard, the technique has now progressed to a consideration of the heat exchange under controlled conditions of an inert atmosphere or of a participating gas.

KINDS OF TRANSFORMATIONS

The endothermic and exothermic deflections of a DTA curve record many kinds of changes of state. The only limitation is that $\frac{\partial Ha}{\partial t}$, the rate of change of enthalpy

(ΔH), be sufficient for the temperature difference to be registered before dissipation in the system. First-order phase changes, which involve discontinuities in volume, entropy, and the first derivatives of the Gibbs function (ΔF) are represented by two kinds: the reversible allotropic inversion of alpha to beta quartz (Faust 1948) (Grimshaw, et al. 1948) and the irreversible monotropic change of aragonite to calcite (Faust 1950). The change from endellite to halloysite probably is a monotropic phase change. Definite second-order phase changes, in which there is no discontinuous change in volume and entropy while the second derivatives of the Gibbs function change discontinuously, are rather rare. One which is habitually recorded in DTA, employing a nickel block as a sample holder, is the change from ferromagnetic to paramagnetic nickel (Curie point) at 353°C.

Murray and White (1949) have discussed the kinetics of thermal dehydration curves. Most of the chemical reactions recorded by DTA are first-order reactions in which the rate of reaction is directly proportional to the concentration of the reacting substance. The dehydration of clay minerals such as kaolinite and the dissociation of

* Publication No. 25, Exploration and Production Technical Division, Shell Oil Co., Houston, Texas.

** Senior Geologist, Exploration and Production Technical Division, Shell Oil Company, Houston 25, Texas.

¹ This apparatus is available commercially from the Eberbach Corporation, Ann Arbor, Michigan.

² Variable pressure DTA apparatus is available from Dr. Robert L. Stone, Austin, Texas.

carbonates are chemical reactions of this type. The very poor curves obtained for muscovite—because the rate of dehydration for the usual heating rates is very slow—also represent a first-order reaction. Second-order reactions in which the rate depends on the concentration of two molecules, and third-order reactions where the concentration of three molecules controls the rate, are not common in the interpretable DTA reactions. Combinations of first- and second-order reactions, and perhaps some third-order reactions, probably take place after the final breakdown of the clay mineral lattice when new high-temperature products are formed.

The kinetics and thermodynamics of the DTA method are actually too complex to permit the application, in any sense other than approximate similarity, of these physical-chemical terms for better-known reactions. This rather incomplete discussion of phase changes and order of chemical reactions is included because it has become increasingly popular to refer to DTA curve deflections as representing a specific kind of chemical reaction or phase change.





FIGURE 1

THERMAL THEORY

Spiel (1945) and Kerr and Kulp (1948), by opposing the thermal effects—the heat of the thermal reaction and the differential heat flow between the block and the sample—arrived at an expression to show that the area enclosed by the loop and the base line is an approximate measure of the total heat effect and, under certain conditions, is proportional to the amount of thermally active material in the sample. By making a set of calibration curves with prepared mixtures of dolomite and calcite, Rowland and Beck (1952) were able to show that this relationship can be used to determine dolomite in limestone when as little as 0.3 percent is present (fig. 13).

Wittels (1951) varied both the heating rate and the mass of the sample to obtain an expression and calibration so that precise calorimetric measurements can be obtained from DTA curves.

M. Vold (1949) has derived equations for the calculation of heats of transformation from differential heating curves, which are independent of external calibration, by using the rate of restoration of a thermal steady state to




DTA CURVES OF SIDERITE

FIGURE 2

establish a relation between the differential temperature and the heat adsorption producing it. Valid results were obtained for such widely differing processes as the melting of stearic acid and the vaporization of water.

A highly significant contribution to the understanding of differential thermal analysis was made by Murray and White (1949). They point out that a Clausius-Clapeyron



DOLOMITE DTA CURVES AT IMM TO 760MM CO2 PRESSURE (AFTER HAUL & HEYSTER, AMER. MIN. 37, 1952)

FIGURE 3




FIGURE 4

type equation can be reduced to a plot of $\ln p_{\text{H}_2\text{O}}$ vs $1/T$ to obtain a straight line of slope $-\Delta H/2R$. By selecting a number of partial pressures of H_2O and observing from the DTA curve the value of $t^\circ\text{C}$. at which the loss of hydroxyl water begins, Stone (1952) assembled data for a van't Hoff line from the slope of which the heat of reaction can be calculated (fig. 1). Comparison of these heats of reaction with values obtained from specific heat data shows that, for minerals of the kaolin group, the temperature at the beginning of the deflection of the DTA curve is considerably higher than equilibrium temperature up to a partial pressure of $\ln p = 6.50$ (665 mm). Above $\ln p = 6.50$ better agreement is obtained. For calcite, good agreement is obtained at $\ln p = 3.8$ (447 mm). Stone concludes from these experiments that at temperatures close to equilibrium in dry air the kaolinite decomposition reaction must be very slow indeed. These experiments show that, even though the clay minerals have very similar structural arrangements, their DTA hydroxyl-loss loops can be shifted selectively by control of the partial pressure of water vapor. Hence, clay mineral DTA curves so obtained should resolve the midrange endothermic loops which interfere when the furnace atmosphere is uncontrolled.

ATMOSPHERE CONTROL

Atmosphere control in differential thermal analysis has taken several different forms. When a sample is heated in air, it builds up its own atmosphere, but not in excess of one atmosphere pressure. A typical example is the dissociation of siderite (Rowland and Jonas 1949) (fig. 2), in which the DTA curve is a compromise between the endothermic effect of CO_2 liberation and the exothermic effect of iron oxidation, until the CO_2 evolution is violent enough to exclude oxygen and the endothermic effect predominates. Oxidation resumes when CO_2 evolution slows down, and the endothermic loop is interrupted by an exothermic loop. A similar effect is shown by the DTA curve when dolomite is heated in air. The curve in air resembles the curve at about 360 mm of CO_2 (Haul 1951) (fig. 3). When a cover is used on the sample holder, the main oxidation loop of siderite is dis-

placed to a higher temperature. Except when the sample well is covered, the pressure of the evolved gas probably never attains one atmosphere pressure and is quickly reduced by diffusion to a much lower concentration. These atmospheric effects are not controlled but are a function of the sample dissociation.

The atmosphere of a furnace may be maintained at about one atmosphere partial pressure by allowing a gas to flow through the furnace (Rowland and Lewis, 1951). This technique is sufficient for many applications where approximately one atmosphere of an inert gas, or a participating gas, is required. A better technique, using a sintered block for a sample holder, has been described by Saunders and Giedroyc (1950). This method insures that the gas surrounds the individual grain of the sample from the beginning of the analysis. Neither of these methods permits control of the partial pressure of the gas, and the composition is maintained only so long as no air is swept in with the gas.

Actual control of the pressure within the furnace has been used as a vacuum technique by Whitehead and Breger (1950). A dynamic system for control of the pressure and composition of the atmosphere surrounding the particles of the sample was described by Stone (1952) who included the sample holder in the gas-handling system. With this arrangement it is possible to maintain a continuous supply of fresh gas moving through the specimen at a predetermined pressure.

Atmosphere control can be used to eliminate unwanted exothermic reactions resulting from the burning of organic matter in clays (fig. 4). DTA curves of some carbonates, particularly calcite and dolomite, are greatly improved by an atmosphere of CO_2 . From DTA curves made in a dynamic steam atmosphere van't Hoff lines can be constructed. While van't Hoff lines constructed from DTA curves only approximate equilibrium at elevated pressures, they are a summary of the DTA curves at several pressures and as such may be more characteristic of the material than the original DTA curve.

DTA CURVES OF CLAYS

Aside from a number of papers describing systematic studies of the collections of clays and carbonate minerals to learn what differences could be observed by this technique, there have been a number of studies involving the factors controlling the individual parts of the differential thermal analysis curves. The geometry of a differential thermal curve of a clay is usually made up of three distinct parts. The first is a low-temperature endothermic loop which is registered when atmospheric water departs from the material. A second or midrange endothermic loop accompanies the loss of bound water or the dissociation of hydroxyls from the lattice. The third is a high-temperature combination of loops accompanying the final breakdown of the lattice and the formation of one or more new materials.

Low-temperature Loop. The low-temperature loop, which may cover the interval from 50°C . to about 240°C ., is dependent on the kind of clay mineral for its presence; on the type (bivalent-univalent) and amount of exchange cations for its shape; and on the moisture content, or the relative humidity surrounding the clay




FIGURE 5

prior to analysis, for its size. In general, members of the kaolinite group do not show a low-temperature peak. The exception is hydrated halloysite; its peak can be irreversibly destroyed by storage over a period of time in an atmosphere of low relative humidity at room temperature, or by heating to slightly more than 100°C.

The three-layer lattice clay minerals invariably have a low-temperature endothermic loop. Of these, the montmorillonite loops are the largest and most sensitive to moisture content, humidity, and type and amount of exchange cations. Although the illites also exhibit a low-temperature loop, the true micas, such as muscovite and biotite, do not. Chlorite in clay-mineral particle size has a low-temperature endothermic loop, but chlorite from metamorphic rocks does not. The effect of exchange cations on montmorillonites and illites is frequently rather marked. Hendricks (1940) pointed out the effect





FIGURE 6

of a number of different exchange cations on different bentonites (fig. 5). In general, clays with monovalent cations exhibit one endothermic loop at about 150°C.; most clays with bivalent cations have a second loop or a shoulder on a loop similar to the monovalent loop at a higher temperature (220°C.). Various organic compounds, particularly those which blanket the space between the layers of the lattice, also have their particular effect on the hydration loop, but this is frequently obscured by the immediate volatilization or burning of the organic material.

As yet, no one has succeeded in making use of the area of the low-temperature endothermic loop to determine either the total moisture content or to make a quantitative estimate of the type and amount of exchange cations on the clay.



DTA CURVES OF DICKITE (OURAY, COLORADO) AT DIFFERENT PRESSURES OF WATER VAPOR (AFTER STONE, J. A. CER 5, 35, 1952)

FIGURE 7

High-temperature Loops. At the high-temperature end of the differential thermogram most of the recorded loops are the combined heat effect of several reactions, both endothermic and exothermic in nature. Grim (1948) and Stone (1952) have pointed out that, even in kaolinite, a very small endothermic loop occurs and is interrupted by the large exothermic loop usually associated with the formation of mullite. The high-temperature zone for members of the montmorillonite and illite groups is largely controlled by the chemical composition of the material. This involves the amount and kind of isomorphic substitution within the lattice and the nature of the exchange cations. Most of the three-layer lattice clay minerals undergo an endothermic reaction associated with the final breakdown of the clay mineral lattice (Grim, 1948) and with the loss of a small amount of water which supposedly results from the loss of the last hydroxyls. Different persons have different ideas as to just what happens during this endothermic reaction. McConnell (1950) theorizes that tetrahedral hydroxyls give rise to the small water loss, and occur in groups of four, substituted for silicon in the tetrahedral layer. It is also possible that the hydroxyls are supplied from local substitution of magnesium in the octahedral layer. While there appears to be no reason for one part of the octahedral layer to retain its character at temperatures

Table 1. Firing products of several clays.

High alumina	900° C.	1000° C.	1100° C.	1200° C.	1300° C.
Kaolinite.....		mullite (a)		mullite (a) cristobalite (b)	
Endellite.....		mullite (a)		mullite (a) cristobalite (b)	
Diaspore.....	α -Al ₂ O ₃ (a)				
Gibbsite.....	γ -Al ₂ O ₃ (u)	α -Al ₂ O ₃ (a)			
Bauxite (Kaolinite and gibbsite)					
Montmorillonite group					
Beidell, Colo.....					mullite cristobalite cristobalite (a) cordierite (a)
Cheto.....		β -quartz (a) anorthite (?) (c)	β -quartz (a) cristobalite (c) anorthite (?) (c)		
Fairview, Utah.....				mullite (a) cristobalite (a)	mullite (a)
Harris Co., Tex.....		spinel (b) cristobalite (c)	cristobalite (a) spinel (a)	cristobalite (a) spinel mullite (b)	cristobalite (a) mullite (b)
Otay, Calif.....		β -quartz (a) enstatite (c)	cristobalite (a) β -quartz (a) enstatite (b)	cristobalite (a) cordierite (a)	cristobalite (c) cordierite (a) periclase (c)
Palmer, Ark.....		spinel (a)	spinel (a) quartz (c)	cristobalite (a) spinel (a) mullite (a)	
Pontotoc Co., Miss.....		spinel (a) α -quartz (b)	cristobalite (a) spinel (a)		cristobalite (b) cordierite (b)
Sierra de Guadalupe.....		spinel (a)	cristobalite (a) spinel (a)	cristobalite (a) spinel (a) cordierite (b)	cristobalite (a) cordierite (a)
Tatatila, Vera Cruz.....		β -quartz (b)			cristobalite (a) mullite (b) cordierite (b)
Upton, Wyo.....	spinel (a)	spinel (a) α -quartz (b)	spinel (a)		mullite (b)
Wagon Wheel Gap, Colo.....	spinel (b)	cristobalite (a) mullite (b) spinel (c)	cristobalite (b)		cristobalite
Woody nontronite					mullite cristobalite spinel

Parenthetic letters signify: (a) important, (b) moderate, and (c) minor. (After Bradley & Grim, 1951.)

higher than that attained by other parts of the same layer, it is still possible to draw the parallel between the temperature at which gibbsite loses its hydroxyls versus the temperature at which brucite loses its hydroxyls. Other magnesium-bearing minerals, such as talc and chlorite, seem also to lose their hydroxyls at tem-

peratures somewhat higher than encountered in materials consisting primarily of aluminum in the octahedral layer.

Bradley and Grim (1951) have described many of the factors controlling the nature of the immediate high-temperature products (table 1). They point out that the




FIGURE 8




FIGURE 9

exchange cations can give rise to a variety of spinels and cordierite. When the exchange ion between the layer positions is blanketed with an organic compound so that at elevated temperatures the only exchange cation present is hydrogen, the formation of mullite occurs even with a three-layer lattice clay mineral. In figure 6 the exothermic loop at 930°C. accompanies the formation of a spinel in the untreated sample, mullite and spinel in the NH_4 sample, and mullite in the remaining samples. In some cases where there is a return to the baseline between the endothermic and exothermic reactions and where lithium is present in the clay mineral, the accompanying excess silica appears in the form of beta quartz instead of cristobalite.

Midrange Loop. The endothermic loop occurring at midtemperature range and associated with the major loss of hydroxyls from the octahedral layer varies considerably from clay to clay. In the kaolinite group this is an intense reaction which probably starts at a much lower temperature but is sufficiently strong to cause deflection at about 450°C. and to peak at about 600°C. Dickite, the most highly organized member of the kaolinite group, has a slightly different differential thermal curve through the range of loss of hydroxyls. The low-temperature side of this loop is quite steep, while the high-temperature side is at a somewhat lesser slope. The result is a loop skewed toward the low-temperature end. The starting and peak temperatures of the midrange loop of both dickite and kaolinite can be shifted by $p_{\text{H}_2\text{O}}$ of the furnace atmosphere (fig. 7). Wyoming bentonite and other bentonitic materials in which the order of stacking and the organization of the crystals are very good, have a loop beginning at about 575°C. and peaking at about 700°C. When the organization is poor, as is the case with most sediments containing montmorillonite, this loop is approximately 100°C. lower. The loop for nontronite, the iron analog of montmorillonite, also occurs at a somewhat lower temperature.

Members of the illite group lose their hydroxyls over the same approximate range as do some of the less well-




FIGURE 10




FIGURE 11

organized montmorillonites. In sediments which may contain both illite and montmorillonite, it is seldom possible to distinguish between montmorillonite and illite with differential thermal curves. In fact, the shales and clays of the Gulf Coast, at least to the base of the Tertiary, appear to contain both an illite and a very poorly organized montmorillonite which may be in effect a degraded illite in which a large portion of the potassium has been lost.

Previously this loss of hydroxyls was considered to be an irreversible reaction. However, Grim and Bradley (1948) (fig. 8) demonstrated that clays heated to a temperature just below the end of their differential thermogram dehydration loop will reabsorb a considerable amount of moisture as hydroxyls when exposed to an average relative humidity over a period of time. From his experiments using steam atmospheres, Stone suggests (fig. 9) that more rehydration may be obtained at elevated steam pressures.

DIFFERENTIAL THERMAL ANALYSIS OF THE CARBONATE MINERALS

The carbonate minerals are especially amenable to differential thermal analysis. Normal anhydrous carbonates undergo dissociation in an atmosphere of CO_2 at progressively lower temperatures in the order Ca, Mg, Mn, Fe, and Zn (fig. 10). The temperature of the dissociation of calcite is very sensitive to the partial pressure of CO_2 . In the absence of CO_2 in the surrounding atmosphere the dissociation starts at about 500°C. When one atmosphere of CO_2 surrounds the sample, the dissociation starts at about 900°C. The other normal carbonates are much less sensitive to change in p_{CO_2} . Rowland and Lewis (1951) have shown that the order of decreasing sensitivity to change in p_{CO_2} is also Ca, Mg, Mn, Fe, and Zn. DTA curves of the anhydrous normal carbonates, with explanations of the reactions represented, have been published by Cutlbert and Rowland (1947), Kerr and Kulp (1948), Gruver (1950), and Beck (1950). In addition to the normal anhydrous carbonates, Beck included DTA curves of samples representative of most of the other carbonate minerals.




FIGURE 12

A review of the interpretations of DTA curves indicates the necessity for: (1) determining by other methods, usually X-ray, the nature of the product formed by each reaction; (2) establishing whether each thermal loop represents a single change or is a compromise heat effect resulting from several reactions; (3) investigating the effect of varying the gas pressure within the sample to establish the temperature dependence of the reaction on the gas phase. The data from (3) when plotted as van't Hoff lines almost uniquely describe the thermal characteristics of the materials.


Calcite. The dissociation of calcium carbonate is used in physical chemistry as a classic example of the effect of the partial pressure of a participating gas on heterogeneous equilibria. Perhaps it is for this reason that very little attention has been given to the DTA curves of calcite. Faust (1950) and Kulp, Kent, and Kerr (1951) have shown that the peak temperature and the initial decomposition temperature of pure calcite decrease when the sample is ground to an extremely fine particle size. Kulp et al. (1951) (fig. 11), also show a drop in both temperatures when the sample is highly diluted with alundum. These results were obtained in an ambient furnace atmosphere without control of the CO_2 and are therefore not definitive. Dilution reduces the opportunity for the buildup of a back pressure of CO_2 and consequently lowers the dissociation temperature. This effect is frequently observed in unwashed Ca-clay samples which have been allowed to stand in water open to the atmosphere. The DTA curves exhibit a small endothermic peak at about 750°C ., resulting from the calcium carbonate formed from calcium in the solution and CO_2 dissolved from the air.

DTA curves of the aragonite \rightarrow calcite transformation have been examined by Faust (1950) (fig. 12), who has pointed out that this monotropic transformation does not take place at a constant temperature, and is subject to further variations resulting from the presence of barium, strontium, lead, and perhaps zinc. The transformation temperatures range from 387°C to 488°C at a heating rate of 12°C per minute.

Magnesite. DTA curves of magnesite have been published by Cuthbert and Rowland (1947), Faust (1949), Gruver (1950), Beek (1950), and Kulp, Kent, and Kerr (1951). Pure coarsely crystalline magnesite heated in air yields a simple endothermic peak at 680 to 700°C . The temperature of the peak varies somewhat in the presence of impurities. The magnesite from Stevens County, Washington, shows an exothermic peak at the

end of the endothermic peak. Kulp attributes this peak to the presence of small amounts of iron substituted in the lattice. It may also be the heat effect accompanying the organization of magnesium oxide as periclase.

Siderite. Cuthbert and Rowland (1947), Kerr and Kulp (1947), Frederickson (1948), and Rowland and Jonas (1949) have discussed the DTA curve of siderite. Diluted and heated in air, this carbonate yields a small exothermic loop (fig. 2). In an atmosphere of CO_2 the loop is large, endothermic, and at the proper temperature for the Ca, Mg, Fe, Mn, and Zn series. Undiluted and heated in air, the curve first swings in the exothermic direction until enough CO_2 has been liberated to prevent oxidation of the iron. The dissociation of CO_2 is then registered by an endothermic loop which is interrupted by an exothermic loop representing the oxidation of the FeO when the back pressure of CO_2 begins to subside. At a higher temperature the partially oxidized iron is completely oxidized to hematite.



DTA Calibration Curves of Small Percentages of Bureau of Standards Dolomite and Iceland Spar Calcite

FIGURE 13




FIGURE 14

Dolomite. Of all of the carbonate minerals of the Ca-Mg-Fe group (Kulp, Kent, and Kerr, 1951) dolomite has received the most attention. Berg (1945) attempted to use the areas under the loops as a quantitative expression of the amount of dolomite in the sample. Rowland and Beck (1952) (fig. 13) succeeded in doing this for samples heated in an atmosphere of CO_2 . Haul and Heystek (1952) (fig. 3) have shown that DTA curves for dolomite have only one loop at 1 mm p_{CO_2} , two loops, resembling the curve made in air, at 300 mm p_{CO_2} , and two distinctly separated loops at one atmosphere of CO_2 . This is accomplished entirely by shifting of the second or CaCO_3 peak. The apparent immobility of the first peak leads them to suggest that this peak is formed only after a certain amount of diffusion of lattice constituents has taken place. The requirement for this activation energy explains the formation of this peak at a higher temperature than the peak for magnesite dissociation.

Actually, the first dissociation peak of dolomite is not immobile. Bradley, Burst, and Graf (1952) (fig. 14) have shown that during prolonged grinding (250 hours) there first appears another peak about 100°C . lower, which grows in size until the usual first peak is exhausted. At any stage the ratio of the sum of the areas of these two peaks to the area of the calcite is constant. These authors demonstrate by X-ray diffraction studies that, by a process of twin gliding and translation gliding, the Ca and Mg of the dolomite lattice which at first occupied alternate positions around any CO_3 group have now been rearranged so that most of the Mg has magnesium for its nearest neighbors and vice versa. Hence, the temperature delay required to activate these atoms to sufficient mobility so that dissociation can occur is no longer required. The first loop of a dolomite DTA curve is the algebraic sum of the ΔH required to dissociate both MgCO_3 and CaCO_3 (endothermic), to reform most of the CaCO_3 (exothermic), and perhaps to form periclase and some calcium oxide (exothermic).

Dolomite furnishes an excellent example of the effect of small crystallites (not fine grain size) on DTA curves. In figure 13 the endothermic loop beginning at 925°C is preceded by a small shoulder. This shoulder accompanies the dissociation of the extremely fine crystallites of CaCO_3 formed from the products of the first loop which

dissociate before the more coarse-grained calcite fragments.

Berg (1943) and Graf (1952) have shown that the presence of soluble salts such as encountered in brines will materially affect the shape and size of the first loop of the dolomite curve. In addition, the presence of a sericite-like mica will completely eliminate the second or calcium carbonate peak in a CO_2 atmosphere.

MISCELLANEOUS APPLICATIONS OF DTA

Soaps. Vold and Vold (1941) established that, instead of melting directly from crystal to liquid, sodium salts of long-chain fatty acids pass through a series of forms, each constituting a definite stable phase existing over a definite range of temperature. They calculated heats of transition from the DTA curves of these soaps and have since (Vold, Grandine, and Vold, 1948) delineated the polymorphic transformations of calcium stearate and calcium stearate monohydrate by their technique.

Greases. By the same technique Vold, Hattiangdi, and Vold (1949) have delineated the phase state and thermal transitions of numerous samples of aluminum, barium, calcium, lithium, sodium, and mixed base commercial greases, and of the corresponding oil-free soaps.

CONCLUSION

Differential thermal analysis is well established as a technique for the characterization and control of materials which undergo characteristic changes on heating. It is less well established as a method for investigating the products obtained when such a material is heated, since equilibrium is an inherent impossibility of the method. However, the latter is not an obstacle when thermodynamic considerations control the design of the apparatus and when good recording equipment is employed. With the addition of dynamic atmosphere control much useful information about the products of heating can be assembled in a short time.

Because differential thermal analysis is most useful when the apparatus is designed so that several different techniques can be employed, there should be no standardization of materials, heating rates, etc. Instead, a flexibility should be maintained so that due consideration can be given to the details of the kind of change being analyzed, and these considerations must be presented as a part of the data.

DISCUSSION

J. A. Pask:

In the DTA curves of montmorillonite Rowland mentioned that the exothermic loop at 930°C . is accompanied by the formation of a spinel in the untreated material, mullite and spinel in the NH_4^+ -saturated samples, and mullite in the methylamine-saturated samples. Could this be discussed?

R. A. Rowland:

I believe the explanation lies in the nature of the exchangeable cation. When the exchangeable cations are Ca^{++} and Mg^{++} , spinel is formed, but when these are completely absent, as in the case of the methylamine-saturated samples, mullite is formed. The formation of both spinel and mullite in the NH_4^+ -saturated sample would indicate that the sample was not completely saturated with NH_4^+ ; some of the original exchangeable cations must have remained on the clay.

J. A. Pask:

Is the spinel formed by a combination of the exchangeable cation and the aluminum of the lattice?

R. A. Rowland:

This appears to be so from the series of curves which I showed and from other curves run in similar fashion.

G. W. Brindley:

I feel that progress can be made in the use of the various methods of clay identification and estimation by a cooperative effort whereby type mineral specimens would be examined by the various methods by those persons who have had a great deal of experience with a given method.

J. A. Pask:

I think that any one of the methods for clay identification is as good and as useful as any other, provided the operator is thoroughly familiar with the method which he uses.

Isaac Barshad:

Each method yields data which another method does not. That is precisely why the various methods of analysis were developed. Thus, while X-ray analysis is indispensable for crystal structure analysis, DTA is indispensable for recording changes which occur in a mineral during the course of heating. It would be practically impossible to identify and estimate amounts of the various clay minerals in a clay sample derived from a soil unless various methods of analysis are used.

T. F. Bates:

This discussion has further indicated the need for additional fundamental research and for the exchange of clay samples between workers on both sides of the Atlantic.

SELECTED REFERENCES

COMPILED BY FRANK J. SANS

- Agafanov, V., and Jourausky, G., 1934, The thermal analysis of the soils of Tunisia: *Pedology, Acad. Sci. Paris, Comptes rendus*, v. 198, pp. 1356-58.
- Agatonoff, V., 1935, Mineralogical study of soil: 3d Internat. Cong. Soil Sci. Trans., v. 3, pp. 74-78.
- Ahrens, P. L., 1950, Differential thermal analysis; a conventional method: 4th Internat. Cong. Soil Sci. Trans., v. 4, pp. 26-27.
- Alexander, L. T., Hendricks, S. B., and Nelson, R. A., 1939, Minerals present in soil colloids; II. Estimation in some representative soils: *Soil Sci.*, v. 43, pp. 273-279.
- Alexander, L. T., Hendricks, S. B., and Faust, G. T., 1941, Occurrence of gibbsite in some soil-forming materials: *Soil Sci. Soc.*, v. 6, pp. 52-57.
- Allaway, W. H., 1948, Differential thermal analyses of clays treated with organic cations as an aid in the study of soil colloids: *Soil Sci. Soc. America Proc.*, v. 13, pp. 183-188.
- Asada, Yahei, 1940, Alunite; VIII, Mechanism of thermal decomposition of alunite: *Inst. Phys. Chem. Research (Tokyo) Bull.*, v. 19, pp. 976-991.
- Ashley, H. E., 1911, The decomposition of clays, and the utilization of smelter and other smoke in preparing sulfates from clays: *Ind. Eng. Chemistry Jour.*, v. 3, pp. 91-94.
- Bailey, F. H., 1952, Thermal differential curves reflect subsurface geology: *World Oil*, v. 134, pp. 77.
- Balandin, A. A., and Patrikeev, V. V., 1944, Differential thermocouple method in contact catalysis: *Acta Physiocochem. (USSR)*, v. 19, pp. 576-591.
- Balandin, A. A., and Patrikeev, V. V., 1944, Differential thermocouple in heterogeneous catalysis: *Jour. Gen. Chemistry (USSR)*, v. 14, pp. 57-69.
- Barshad, I., 1948, Vermiculite and its relation to biotite as revealed by base-exchange reactions, X-ray, differential thermal curves, and water content: *Am. Mineralogist*, v. 33, pp. 655-678.
- Barshad, I., 1950, The effect of the interlayer cations on the expansion of the mica type of crystal lattice: *Am. Mineralogist*, v. 35, pp. 225-239.
- Barshad, I., 1952, Temperature and heat of reaction calibration of the differential thermal analysis apparatus: *Am. Mineralogist*, v. 37, pp. 667-695.
- Beck, C. W., 1946, An improved method of differential thermal analysis and its use in the study of natural carbonates: Ph.D. Thesis, Harvard Univ.
- Beck, C. W., 1950, An amplifier for differential thermal analysis: *Am. Mineralogist*, v. 35, pp. 508-524.
- Beck, C. W., 1950a, Differential thermal analysis curves of carbonate minerals: *Am. Mineralogist*, v. 35, pp. 985-1013.
- Beck, W. R., 1949, Crystallographic inversions of the aluminum orthophosphate polymorphs and their relation to those of silica: *Am. Ceramic Soc. Jour.*, v. 32, pp. 147-151.
- Belyankin, D. S., and Deodot'ev, K. M., 1949, The heating curve of kaolin in a new light: *Doklady Akad. Nauk. (USSR)*, v. 65, pp. 357-360.
- Berg, L. G., 1943, Influence of salt admixtures upon dissociation of dolomite: *Doklady Acad. Sci. (USSR)*, v. 38, pp. 24-27.
- Berg, L. G., Nikolaiev, V. I., and Rode, E. Y., 1944, Thermographia: *Acad. Sci. (USSR)*, v. 25.
- Berg, L. G., 1945, On area measurements in thermograms for quantitative estimations and the determination of heats of reaction: *Doklady Acad. Sci. (USSR)*, v. 49, pp. 648-651.
- Berg, L. G., and Rassonskaya, I. S., 1950, Rapid thermal analysis: *Doklady Akad. Nauk. (USSR)*, v. 73, pp. 113-115.
- Berg, L. G., and Rassonskaya, I. S., 1951, Thermographic analysis under elevated pressures: *Doklady Akad. Nauk. (USSR)*, v. 81, pp. 855-858.
- Berkelhamer, L. H., 1944, Differential thermal analysis of quartz: *U. S. Bur. Mines Rept. Inv. 3763*, 18 pp.
- Berkelhamer, L. H., 1945, An apparatus for differential thermal analysis: *U. S. Bur. Mines, Tech. Paper 664*, pp. 38-55. . . . 1944, *U. S. Bur. Mines Rept. Inv. 3762*, 11 pp.
- Berkelhamer, L. H., and Speil, S., 1945, Differential thermal analysis: *Mine and Quarry Eng.*, v. 10, pp. 221-225.
- Berkelhamer, L. H., and Speil, S., 1945, II. Differential thermal analysis: *Mine and Quarry Eng.*, v. 10, pp. 273-279.
- Bradley, W. F., and Grim, R. E., 1948, Colloid properties of layer silicates: *Jour. Phys. and Colloid Chemistry*, v. 52, pp. 1404-1413.
- Bradley, W. F., and Grim, R. E., 1951, High temperature thermal effects of clay and related materials: *Am. Mineralogist*, v. 36, pp. 182-201.
- Bradley, W. F., 1952, The alternating layer sequence of rectorite: *Am. Mineralogist*, v. 35 (7, 8), pp. 590-596.
- Bradley, W. F., Burst, J. F., and Graf, D. L., 1953, The crystal chemistry and differential thermal effects of dolomite: *Am. Mineralogist*, v. 38, pp. 207-217.
- Bramao, L., Cady, J. G., Hendricks, S. B., and Swerdlow, M., 1952, Criteria for the characterization of kaolinite, halloysite, and a related mineral in clays and soils: *Soil Sci.*, v. 73, pp. 273-287.
- Burgess, G. K., 1908, On methods of obtaining cooling curves: *Electro-chem. Metal Ind.*, v. 6, pp. 366-371.
- Burgess, G. K., 1908-09, Methods of obtaining cooling curves: *U. S. Bur. Standards, Tech. News Bull.* 5, pp. 199-225.
- Caillere, S., 1933, Study of the thermal dissociation of serpentine minerals: *Acad. Sci. Paris, Comptes rendus*, v. 196, pp. 628-630.
- Caillere, S., 1934, Observation of the chemical composition of palygorskites: *Acad. Sci. Paris, Comptes rendus*, v. 198, pp. 1795-1798.
- Caillere, S., 1936, Study of the serpentine minerals: *Soc. franc. Minéralogie Bull.*, v. 59, pp. 163-326.
- Caillere, S., and Henin, S., 1939, Differential thermal analysis of kaolinite: *Acad. Sci. Paris Comptes rendus*, v. 209, pp. 684-686.
- Caillere, S., and Henin, S., 1944, New observations of faratsihite: *Acad. Sci. Paris Comptes rendus*, v. 219, pp. 485-489.
- Caillere, S., and Henin, S., 1944a, The origin of some anomalies presented by the thermal curves of certain montmorillonites: *Acad. Sci. Paris Comptes rendus*, v. 219, pp. 685-686.
- Caillere, S., Henin, S., and Ture, L., 1946, Investigations in differential thermal analysis of clays—significance and specificity of the phenomenon of recrystallization: *Acad. Sci. Paris Comptes rendus*, v. 223, pp. 383-384.
- Caillere, S., and Henin, S., 1947, The application of differential thermal analysis to the study of the clay minerals found in soils: *Ann. Agron.*, v. 17, pp. 23-72.
- Caillere, S., Guennelon, R., and Henin, S., 1949, Thermal behavior of some phyllites at 14 angstrom units: *Acad. Sci. Paris Comptes rendus*, v. 228, pp. 933-935.
- Caillere, S., Henin, S., and Esquevin, J., 1950, The hydration of certain phyllitic minerals—metahalloysite: *Acad. Sci. Paris Comptes rendus*, v. 230, pp. 1190-1192.
- Caillere, S., and Henin, S., 1951, Observations on the chlorites of iron ores: *Clay Min. Bull.*, v. 5, pp. 134-138.

- Caillere, S., and Henin, S., 1951a, The properties and identification of saponite (bowlingite): *Clay Min. Bull.*, v. 5, pp. 138-145.
- Callaghan, E., 1948, Endellite deposits in Gardner mine ridge, Lawrence County, Indiana: *Indiana Div. Geology Bull.* 1, 47 pp.
- Chiang, Y., and Smothers, W. J., 1952, Differential thermal analysis in the general chemistry laboratory: *Jour. Chem. Ed.*, v. 29, pp. 308-309.
- Chukhrov, F. V., 1950, Beudantite from the Kazakhstan steppe: *Doklady Akad. Nauk. (USSR)*, v. 72, pp. 115-117.
- Chukhrov, F. V., and Anosov, F. Y., 1950, Medmontite, a copper-bearing montmorillonite mineral: *Zapiski Vsesoyuz. Mineral. Obshchestva*, v. 79, pp. 23-27.
- Chukhrov, F. V., and Anosov, F. Y., 1950a, On the nature of chrysocolla: *Mem. Soc. Russe Min.*, v. 79, pp. 127-136.
- Cohn, W. H., 1924, The problem of heat economy in the ceramic industry: *Am. Ceramic Soc. Jour.*, v. 7, pp. 475-488.
- Collini, B., 1950, The mineralogical composition of our (Swedish) Quaternary clays: *Geol. Foren. i Stockholm Forh.*, v. 72, pp. 192-206.
- Cuthbert, F. L., 1944, Clay minerals in Lake Erie sediments: *Am. Mineralogist*, v. 29, pp. 378-388.
- Cuthbert, F. L., 1946, Differential thermal analysis of New Jersey clays: *New Jersey Dept. Conservation, Misc. Geol. Paper*, 20 pp.
- Cuthbert, F. L., and Rowland, R. A., 1947, Differential thermal analysis of some carbonate minerals: *Am. Mineralogist*, v. 32, pp. 111-116.
- Dean, L. A., 1947, Differential thermal analysis of Hawaiian soils: *Soil Sci.*, v. 63, pp. 95-105.
- Dennis, T. W., and Hunt, J. M., 1949, Application of certain instrumental methods on production research: *World Oil*, v. 129, pp. 152-154, 158.
- Dubois, P., 1936, Thermal balance analyzer with photo-recorder: *Soc. Chem. France Bull.*, v. 3, pp. 1178-1181.
- Efremov, N. E., 1940, The problem of classification of serpentine minerals by the method of thermal analysis: *Acad. Sci. USSR, Comptes rendus*, v. 28, pp. 442-445.
- Ewell, R. H., Bunting, E. N., and Geller, R. F., 1936, Thermal decomposition of talc: *U. S. Bur. Standards, Jour. Research*, v. 15, pp. 551-556 (Research Paper 848).
- Faust, G. T., 1944, The differentiation of magnesite from dolomite in concentrates and tailings: *Econ. Geology*, v. 39, pp. 142-151.
- Faust, G. T., 1948, Thermal analysis of quartz and its use in calibration in thermal analysis studies: *Am. Mineralogist*, v. 33, pp. 337-345.
- Faust, G. T., 1949, Dedolomitization and its relation to a possible derivation of a magnesium-rich hydrothermal solution: *Am. Mineralogist*, v. 34, pp. 789-823.
- Faust, G. T., 1949a, Differentiation of aragonite from calcite by differential thermal analysis: *Science, new ser.*, v. 110, pp. 402-403.
- Faust, G. T., 1950, Thermal analysis studies on carbonates; I. Aragonite and calcite: *Am. Mineralogist*, v. 35, pp. 207-224.
- Faust, G. T., 1951, Thermal analysis and X-ray studies of saucinite and some zinc minerals of the same paragenetic association: *Am. Mineralogist*, v. 36, pp. 795-823.
- Fedot'ev, K. N., 1940, Modern methods of thermal analysis. A method for registering heating curves: *Trudy Tref'ego Soveshchaniya Eksptl. mineral i Petrog. Inst. Geo. Nauk*, pp. 83-94 ... 1941, *Khim. Referat.* 3 hur 4, no. 2, p. 57.
- Fenner, C. N., 1913, Stability relations of silica minerals: *Am. Jour. Sci.*, v. 36, pp. 331-384.
- Ferrandis, V. A., 1949, Differential thermal analysis of some Spanish clays and kaolins: *Anales edafol. y fisiol. vegetal (Madrid)*, v. 8, pp. 33-58.
- Fink, W. L., Van Horn, K. R., and Pafour, H. A., 1931, Thermal decomposition of alunite: *Ind. Eng. Chem.*, v. 23, 1248-50 ... 1932, *Ceramic Abst.*, v. 11 No. 4, p. 274.
- Franzen, P., and Van Voorthuysen, J. J. B., 1950, Synthesis of nickel hydrosilicates: *4th Int. Cong. Soil Sci. Trans.*, v. 3, pp. 34-37.
- Frederickson, A. J., 1948, Differential thermal curve of siderite: *Am. Mineralogist*, v. 33, pp. 372-374.
- Frueh, A. J., Jr., 1950, Disorder in the mineral bornite, Cu_5FeS_4 : *Am. Mineralogist*, v. 35, pp. 185-192.
- Gad, G. M., 1950, Thermochemical changes in alunite and alunite clays: *Am. Ceramic Soc. Jour.*, v. 33, pp. 208-210.
- Gilard, P., Jr., 1950, Several particular aspects of the treatment of kaolin and metakaolin in autoclave: *COBEA*, no. 4.
- Ginzburg, A. I., 1950, Kruzhanovskite, a new phosphate mineral: *Doklady Akad. Nauk. (USSR)*, v. 72, pp. 763-766.
- Gorboinov, N. O., and Shurygina, E. A., 1950, Thermal curves of minerals encountered in soils and rocks: *Pochvovedenie (pedology) (USSR)*, pp. 367-373.
- Graf, D. L., 1952, Preliminary report on the variations in differential thermal curves of low-iron dolomites: *Am. Mineralogist*, v. 37, pp. 1-27.
- Granger, A., 1934, Thermal analysis of clay: *Ceramique*, v. 37, p. 58.
- Granquist, W. T., and Amero, R. C., 1948, Low temperature nitrogen adsorption studies on attapulgite (Floridin): *Am. Chem. Soc. Jour.*, v. 70, p. 3265.
- Griffiths, J. C., 1946, Clay research and oil development problems: *Jour. Inst. Pet.*, v. 32, no. 265, pp. 18-31.
- Grim, R. E., and Bradley, W. F., 1940, Investigation of effect of heat on clay minerals, illite and montmorillonite: *Am. Ceramic Soc. Jour.*, v. 23, pp. 242-248; *Illinois Geol. Survey. Rept. Inv.* 66, 13 pp.
- Grim, R. E., 1942, Modern concepts of clay minerals: *Jour. Geology*, v. 50, pp. 225-275.
- Grim, R. E., and Rowland, R. A., 1942, Differential thermal analysis of clay minerals and other hydrous materials: *Am. Mineralogist*, v. 27, pp. 746-761, 801-18 ... *Illinois Geol. Survey, Rept. Inv.* 85.
- Grim, R. E., and Rowland, R. A., 1944, Differential thermal analysis of clays and shales, control and prospecting method: *Am. Ceramic Soc. Jour.*, v. 27, pp. 65-76.
- Grim, R. E., Machin, J. S., and Bradley, W. F., 1945, Amenable-ability of various types of clay minerals to alumina extraction by the lime sinter and lime soda sinter processes: *Illinois Geol. Survey Bull.*, v. 69, pp. 9-77.
- Grim, R. E., 1947, Differential thermal curves of prepared mixtures of clay minerals: *Am. Mineralogist*, v. 32, pp. 493-501 ... 1948, *Illinois Survey, Rept. Inv.* 134.
- Grim, R. E., and Bradley, W. F., 1948, Rehydration and dehydration of the clay minerals: *Am. Mineralogist*, v. 33, pp. 50-59.
- Grim, R. E., Dietz, R. S., and Bradley, W. F., 1949, Clay mineral composition of some sediments from the Pacific Ocean off the California Coast and the Gulf of California: *Geol. Soc. America Bull.*, v. 60, pp. 1785-1808.
- Grimshaw, R. W., and Roberts, A. L., 1944, Study of the clay quartz system—estimation of quartz by thermal methods: *Gas Research Board, Communication* 19, pp. 31-38.
- Grimshaw, R. W., Heaton, E., and Roberts, A. L., 1945, Constitution of refractory clays; II. Thermal analysis methods: *British Ceramic Soc. Trans.*, v. 44 (6), pp. 76-92. *Ceram. Abstracts*, 1946, April, p. 66.
- Grimshaw, R. W., and Roberts, A. L., 1946, Study of the clay quartz system; II. Thermal analysis methods—experiments with tridymite and cristobalite: *Gas Research Board, Communication* 25, pp. 58-62.
- Grimshaw, R. W., and Roberts, A. L., 1948, Study of the clay quartz system; IV. Extension of the thermal analysis method to quartzite rocks: *Gas Research Board, Communication* 41, pp. 21-6.
- Grimshaw, R. W., Westerman, A., and Roberts, A. L., 1948, A symposium on silica inversions; I. Thermal effects accompanying the inversion of silica: *British Ceramic Soc. Trans.*, v. 47, pp. 269-276.
- Gruver, R. M., 1948, Precision method of thermal analysis: *Am. Ceramic Soc. Jour.*, v. 31, pp. 323-328.
- Gruver, R. M., Henry, E. C., and Heystek, H., 1949, Suppression of thermal reactions in kaolinite: *Am. Mineralogist*, v. 34, pp. 869-873.
- Gruver, R. M., 1950, Differential thermal analysis studies of ceramic materials; I. Characteristic heat effects of some carbonates: *Am. Ceramic Soc. Jour.*, v. 33, pp. 96-101.
- Gruver, R. M., 1950a, Differential thermal analysis studies of ceramic materials; II. Transition of aragonite to calcite: *Am. Ceramic Soc. Jour.*, v. 33, pp. 171-174.
- Gruver, R. M., and Henry, E. C., 1950, Differential thermal analysis, a useful tool in ceramic research: *Pennsylvania State College, Mineral Inds.*, v. 20, pp. 3-4.
- Gruver, R. M., 1951, Differential thermal analysis studies of ceramic materials; III. Characteristic heat effects of some sulfates: *Am. Ceramic Soc. Jour.*, v. 34, pp. 353-357.
- Haffray, J., and Viloteau, J., 1948, The thermal and dilatometric analysis of chromic oxide: *Acad. Sci. Paris, Comptes rendus*, v. 226, pp. 1701-1702.

- Hall, J. L., 1941, Secondary expansion of high alumina refractories: *Am. Ceramic Soc. Jour.*, v. 24, pp. 349-356.
- Harman, C. G., and Fraulini, Felix, 1940, Properties of kaolinite as a function of its particle size: *Am. Ceramic Soc. Jour.*, v. 23 (9), pp. 252-359.
- Harman, C. G., and Parmalee, C. W., 1942, Testing and classification of ballclays; Thermal history: *Am. Ceramic Soc., Bull.* 21 (11), pp. 283-86.
- Hattiangdi, G. S., Vold, M. J., and Vold, R. D., 1949, differential thermal analysis of metal soaps: *Ind. Eng. Chem.*, v. 41, pp. 2320-2324.
- Iaul, Robert A. W., and Heystek, Hendrick, 1952, Differential thermal analysis of the dolomite decomposition: *Am. Mineralogist*, v. 37, pp. 166-180.
- Hedvall, J. A., Lindner, R., and Hartler, N., 1950, A thermal-analysis study of the crystallographic transition of silver sulfate: *Acta Chem. Scand.*, v. 4, pp. 1099-1108.
- Hendricks, S. B., and Alexander, L. T., 1939, Minerals present in soil colloids; I. Description and methods for identification; *Soil Sci.*, v. 48, pp. 257-271.
- Hendricks, S. B., and Alexander, L. T., 1940, Semiquantitative estimation of montmorillonite in clays: *Soil Sci. Soc. America Proc.*, v. 5, pp. 95-99.
- Hendricks, S. B., Nelson, R. A., and Alexander, L. T., 1940, Hydration mechanism of the clay mineral montmorillonite saturated with various cations: *Am. Chem. Soc. Jour.*, v. 62, pp. 1457-1464.
- Hendricks, S. B., 1941, Base exchange of the clay mineral montmorillonite for organic cations and its dependence upon absorption due to van der Waal's forces: *Jour. Phys. Chemistry*, v. 45, pp. 65-81.
- Hendricks, S. B., Goldich, S. S., and Nelson, R. A., 1946, A portable differential thermal analysis unit for bauxite exploration: *Econ. Geology*, v. 41, pp. 64-76.
- Herold, P., and Planje, T. J., 1948, Modified differential thermal analysis apparatus: *Jour. Am. Ceramic Soc.*, v. 31, pp. 20-22.
- Heystek, R., 1952, Differential thermal analysis of gangue minerals in chrome oven: *Am. Ceramic Soc. Bull.*, v. 31, pp. 133-138.
- Hill, W. L., Arminger, W. H., and Gooch, S. D., 1950, Some properties of pseudowavellite from Florida: *Min. Eng.*, v. 187, pp. 699-702.
- Hollings, H., and Cobb, J. W., 1915, Thermal phenomena in carbonization: *J. Gas Lighting*, 126, 917-24; *Gas World*, v. 60, pp. 872-878.
- Hollings, H., and Cobb, J. W., 1915, Thermal study of the carbonization process: *Chem. Soc. Jour.*, v. 107, pp. 1106-1115.
- Honeyborne, D. B., 1951, The clay minerals in the Keuper marl: *Clay Min. Bull.*, v. 5, pp. 150-157.
- Houldsworth, H. S., and Cobb, J. W., 1922-23, Behavior of fireclays, bauxites, etc., on heating: *British Ceramic Soc. Trans.*, v. 22, pp. 111-137, 344-348.
- Howie, T. W., and Lakin, J. R., 1947, A note on the application of the differential thermal method to some basic refractory materials: *British Ceramic Soc. Trans.*, v. 46, pp. 14-22.
- Hummel, F. A., 1949, Properties of some substances isostructural with silica: *Am. Ceram. Soc. Jour.*, v. 32, pp. 320-326.
- Hurlbut, C. S., Jr., 1946, Artinite from Luning, Nevada: *Am. Mineralogist*, v. 31, pp. 365-369.
- Insley, H., and Ewell, R. H., 1935, Thermal behavior of the kaolin minerals: *U. S. Bur. Standards, Jour. Research*, v. 14, pp. 615-627 (Research Paper 792).
- Ivanova, V. P., 1946, On the mineralogy of hydrated ferri-aluminosilicates: *Acad. Sci. (USSR)*, pp. 93-103.
- Ivanova, V. P., and Tatarskii, V. B., 1950, Thermograms of mixtures of dolomite and kaolin: *Doklady Akad. Nauk. (USSR)*, v. 73, pp. 341-343.
- Jaffray, J., 1947, The investigation of higher order transformations by thermal analysis: *Jour. Recherches centr. Nat'l Recherche sci.*, pp. 153-163.
- Jeffries, C. D., 1944, Quantitative approach to the study of thermal characteristics of clays: *Soil Sci. Soc. America Proc.*, v. 9, pp. 86-91.
- Johnson, A. L., 1949, Surface area and its effect on exchange capacity of montmorillonite: *Am. Ceramic Soc. Jour.* v. 32, pp. 210-214.
- Jourdain, A., 1937, Studies of the constituents of refractory clays by means of thermal analysis: *Ceramique*, v. 40, pp. 135-141.
- Kagan, Y. B., and Bashkirov, A. N., 1948, Use of the differential thermocouple for kinetic measurements: *Izvest. Akad. Nauk. (USSR), Otdel, Tekh. Nauk.*, pp. 349-358.
- Kauffman, A. J., Jr., 1948, Differential thermal analysis: *World Oil*, v. 128, no. 3, pp. 118, 120, 122, 124, 126.
- Kauffman, A. J., Jr., 1949, Differential thermal analysis as applied to the lime-soda sinter process: *U. S. Bur. Mines Rept. Inv.* 4585.
- Kauffman, A. J., Jr., and Dilling, E. D., 1950, Differential thermal curves of certain hydrous and anhydrous minerals, with a description of the apparatus used: *Econ. Geology*, v. 45, pp. 222-244.
- Kazakov, A. V., and Andrianov, K. S., 1936, Methods of thermal analysis: *Acad. V. I. Vernadskommu k Pyatides-syatiletiiyu Nauch. Devatelnosti*, 2, 833-58 . . . 1938, *Chem. Zentralbl.* I, pp. 2305-2306.
- Keller, W. D., and Westcott, J. F., 1948, Differential thermal analysis of some Missouri fireclays: *Am. Ceramic Soc. Jour.*, v. 31, pp. 100-105.
- Kelley, W. P., and Page, J. B., 1942, Criteria for the identification of the constituents of soil colloids: *Soil Sci. Soc. America Proc.*, v. 7, pp. 175-181.
- Kerr, P. F., and Kulp, J. L., 1947, Differential thermal analysis of siderite: *Am. Mineralogist*, v. 32, pp. 678-680.
- Kerr, P. F., and Kulp, J. L., 1948, Multiple differential thermal analysis: *Am. Mineralogist*, v. 33, pp. 387-419.
- Kerr, P. F., Kulp, J. L., and Hamilton, P. K., 1949, Differential thermal analysis of reference clay mineral specimens: *API Proj. 49, Prelim. Rept. 3*, Columbia Univ.
- Kerr, P. F., and Holland, H. D., 1951, Differential thermal analysis of davidite: *Am. Mineralogist*, v. 36, pp. 563-573.
- Kind, V. A., Okorokov, S. D., and Khodikel, E. P., 1939, The use of the method of thermal analysis: *Tsement* 6, no. 7, pp. 32-37.
- Kiyoura, R., and Sata T., 1950, The quantitative analysis of the $\text{CaCO}_3 - \text{Ca}(\text{OH})_2 - \text{Mg}(\text{OH})_2$ system by differential thermal analysis: *Ceramic Assoc. Japan Jour.*, v. 58.
- Knizek, J. O., and Fetter, H., 1946, Properties of natural alunitic clays: *Am. Ceramic Soc. Jour.*, v. 29, pp. 308-313.
- Knizek, J. O., and Fetter, H., 1947, Alunite and clays: *British Ceramic Soc. Trans.*, v. 46, pp. 22-46.
- Kournakov, N. S., and Tchernick, V. V., 1928, Physical-chemical investigation of several hydrated iron oxides and clay silicates: *Soc. Russ. Mineral. Mem. LVII*, pp. 62-73.
- Kracek, F. C., 1929, The polymorphism of sodium sulfate: *I. Thermal analysis: Jour. Phys. Chemistry*, v. 33, pp. 1281-1303.
- Kracek, F. C., Bowen, N. L., and Morey, G. W., 1929, The system: potassium metasilicate-silica: *Jour. Phys. Chemistry*, v. 33, pp. 1857-1879.
- Kracek, F. C., 1946, Phase relations in the system sulfur-silver and the transitions in silver sulfide: *Am. Geophysical Union Trans.*, v. 27, pp. 364-374.
- Kulp, J. L., and Kerr, P. F., 1947, Multiple thermal analysis: *Science (new ser.)*, v. 105, pp. 413-414.
- Kulp, J. L., Wright, H. D., and Holmes, R. J., 1949, Thermal study of rhodochrosite: *Am. Mineralogist*, v. 34, pp. 195-219.
- Kulp, J. L., and Kerr, P. F., 1949, Improved differential thermal apparatus: *Am. Mineralogist*, v. 34, pp. 839-845.
- Kulp, J. L., and Adler, H. H., 1950, Thermal study of jarosite: *Am. Jour. Sci.*, v. 248, pp. 475-487.
- Kulp, J. L., and Trites, A. F., 1951, Differential thermal analysis of natural hydrous ferric oxides: *Am. Mineralogist*, v. 36, pp. 23-45.
- Kulp, J. L., Kent, P., and Kerr, P. F., 1951, Thermal study of the Ca-Mg-Fe carbonate minerals: *Am. Mineralogist*, v. 36, pp. 643-671.
- Kumanin, K. G., and Kalenen, N. S., 1936, The effect of some experimental factors on the geometrical elements of heating curves: *Jour. Phys. Chem. (USSR)*, v. 7, pp. 405-417.
- Kurnakov, N. S., and Uraxov, G. G., 1924, Heating curves of Tichvinski bauxites: *Ann. Inst. Phys. Chem. Anal. Leningrad*, v. 2, pp. 495-496.
- Kurnakov, N. S., and Uraxov, G. G., 1924, Thermal analysis of clays and bauxites: *Ann. Inst. Phys. Chem. Anal. Leningrad*, v. 2, pp. 496-498.
- Kurylenko, C., 1950, Thermal analysis of several tourmalines: *Soc. Franc. mineral. Bull.*, v. 73, pp. 49-54.
- Laird, J. S., and Geller, R. F., 1919, Rehydration of calcined clay: *Am. Ceramic Soc. Jour.*, v. 2 (10), pp. 828-832.
- Lazarenko, E. K., 1950, Mineralogical characteristics of donbas-site: *Doklady Akad. Nauk. (USSR)*, v. 72, pp. 771-774.
- Le Chatelier, H., 1887, The constitution of clay: *Zeitschr. physik. Chem.*, v. 1, p. 396.
- Le Chatelier, H., 1887, The action of heat on clays: *Soc. Franc. Mineral. Bull.*, v. 10, pp. 204-211.

- Leont'eva, A. A., 1944, An attempt to apply thermal analysis to the study of adsorption processes: *Jour. Phys. Chem. (USSR)*, v. 18, pp. 469-472.
- Linseis, M., 1950, Relation between mineralogical structure and ceramic properties of kaolins and clay: *Sprechsaal*, v. 83, pp. 253-256, 389-391, 409-410, 433-436, 456-458.
- Luzhnikov, L. P., and Berg, L. G., 1948, Use of differential thermography in the study of aging in aluminum alloys: *Zavodskaya Lab.*, v. 14, pp. 824-828.
- McConnell, Duncan, 1950, The crystal chemistry of montmorillonite: *Am. Mineralogist*, v. 35, pp. 166-173.
- McConnell, Duncan, 1951, The crystal chemistry of montmorillonite; II Calculation of the structural formula: *Clay Min. Bull.*, v. 6, pp. 179-189.
- McConnell, D., and Early, J. W., 1952, Apparatus for differential thermal analysis: *Am. Ceramic Soc. Jour.*, v. 34, (6), pp. 183-187.
- Magee, A. E., 1926, The heat required to fire ceramic bodies: *Am. Ceramic Soc. Jour.*, v. 9, pp. 206-247.
- Mackenzie, R. C., 1949, Nature of free iron oxides in soil clays: *Nature*, v. 164, p. 244.
- Mackenzie, R. C., 1950, Differential thermal analysis of clay minerals: 4th Int. Cong. Soil Sci. Trans., v. 2, pp. 55-59.
- Mackenzie, R. C., 1951, Differential thermal analysis and its application to industrial powders: *Tonind. Zeit.*, v. 75, pp. 334-340.
- Manly, R. L., Jr., 1950, The differential thermal analysis of certain phosphates: *Am. Mineralogist*, v. 35, pp. 108-115.
- Mellor, J. W., and Holderoft, A. D., 1911, The chemical constitution of the kaolinite molecule: *Pottery Gazette*, v. 36, pp. 680-686. . . . *British Ceramic Soc. Trans.*, v. 10, pp. 94-120.
- Menshutkin, B. N., 1936, History of thermal analysis: *Ann. secteur. Anal. Phys. Chem., Inst. Chem. gen. (USSR)*, v. 8, pp. 373-406. . . . *Chem. Abstracts*, v. 30, p. 5886.
- Mitchell, L., and Henry, E. C., 1943, Nature of Georgia kaolin; II. Mineral analysis: *Am. Ceramic Soc. Jour.*, v. 26, pp. 113-119.
- Mitchell, L., 1950, A new classification of the clays of Georgia: Georgia Div. Conservation, Dept. Mines, Mining, and Geol. Survey, Bull. 56, pp. 96-98.
- Murray, P., and White, J., 1949, The kinetics of clay decomposition: *Clay Min. Bull.* 3, pp. 84-88. . . . *British Ceramic Soc. Trans.*, v. 48, pp. 187-206.
- Nagai, S., Asahara, T., and Imai, M., 1943, Studies on high alumina minerals; I. Thermal analysis: *Japan. Ceramic Assoc. Jour.*, v. 51, pp. 381-384.
- Nagelschmidt, G., 1939, The identification of minerals in soil colloids: *Jour. Agr. Sci.*, v. 29, pp. 476-501.
- Nagy, R., and Chung, K. L., 1947, Thermal and X-ray analyses of some common phosphors: *Optical Soc. America Jour.*, v. 37, pp. 37-41.
- Norin, R., 1944, The decomposition products of kaolinite: *Geol. Forh. Foren.*, v. 66, pp. 15-18.
- Norin, R., 1944, Experiments in calculating the actual mineralogical composition of ceramic silica bricks by the aid of differential thermal analysis: *The Svedburg (mem. vol.)*, pp. 189-192.
- Norton, F. H., 1939, Critical study of the differential thermal method for identification of clay minerals: *Am. Ceramic Soc. Jour.*, v. 22, pp. 54-63.
- Norton, F. H., 1939, Hydrothermal formation of clay minerals in the laboratory: *Am. Mineralogist*, v. 24, pp. 1-18.
- Norton, F. H., 1940, Analysis of high-alumina clays by the thermal method: *Am. Ceramic Soc. Jour.*, v. 23, pp. 281-282.
- Nutting, P. G., 1943, Some standard thermal dehydration curves of minerals: U. S. Geol. Survey, Prof. Paper 197-E, pp. 197-217.
- Orcel, J., 1927, Thermal analyses of chlorites: *Soc. franc. mineral Bull.*, v. 50, pp. 278-322. . . . *Acad. Sci. Paris, Comptes rendus*, v. 183, pp. 565-567.
- Orcel, J., 1930, Thermal analysis of chlorite: *Soc. franc. mineral Bull.*, v. 52, pp. 194-197.
- Orcel, J., and Caillere, S., 1933, Differential thermal analysis of montmorillonite (bentonite): *Acad. Sci. Paris, Compt. rend.*, v. 197, pp. 774-777.
- Orcel, J., 1935, Use of differential thermal analysis for determination of the constituents of clays, laterites and bauxites: *Congr. Internal. Mines Met. Geol. Appl.*, 7 Session, Paris, Oct. 1935, *Geology*, v. 1, pp. 359-373.
- Page, J. B., 1943, Differential thermal analysis of montmorillonite: *Soil Sci.*, v. 56, pp. 273-283.
- Partridge, E. P., Hicks, V., and Smith, G. W., 1941, a thermal, microscopic and X-ray study of the system $\text{Na}_3\text{PO}_4\text{-Na}_4\text{P}_2\text{O}_7$: *Am. Chem. Soc. Jour.*, v. 63, p. 454.
- Pask, J. A., and Davies, B., 1943, Thermal analysis of clay minerals and acid extraction of alumina from clays: U. S. Bur. Mines Rept. Inv. 3737.
- Pavlovitch, S., 1935, The action of heat upon some natural oxides of manganese: *Acad. Sci. Paris, Comptes rendus*, v. 200, pp. 71-73.
- Perkins, A. T., 1948, Kaolin and treated kaolins and their reactions: *Soil Sci.*, v. 65, pp. 185-191.
- Reviere, A., 1946, Argillaceous sediments: *Soc. Geol. Franc. Bull.*, v. 16, pp. 43-55.
- Rice, A. P., 1949, Differential thermal analysis studies in some silicate systems: *Electrochem. Soc. Jour.*, v. 96, 114-122.
- Roberts-Austen, 1899, Fifth report of the alloys research committee: *Inst. Mech. Eng.*, v. 35.
- Roberts, A. L., 1949, Differential thermal analysis applied to the silica minerals: (Univ. of Leeds) 3rd Anv. meet., *Min. Soc.*, Apr.
- Rowland, R. A., 1948, Differential thermal analysis apparatus: Shell Oil Co., Exploration and Production Research Division Rep. 101. 41 pp.
- Rowland, R. A., and Jonas, E. C., 1949, Variations in Differential thermal analysis curves of siderite: *Am. Mineralogist*, v. 34, pp. 550-558.
- Rowland, R. A., and Lewis, D. R., 1951, Furnace atmosphere control in differential thermal analysis: *Am. Mineralogist*, v. 36 (1 & 2), pp. 80-91.
- Rowland, R. A., and Beck, C. W., 1952, Determination of small quantities of dolomite by differential thermal analysis: *Am. Mineralogist*, v. 37, pp. 76-82.
- Roy, R., Middlesworth, E. T., and Hummel, F. A., 1948, Mineralogy and thermal behavior of phosphates; I. Magnesium pyrophosphate: *Am. Mineralogist*, v. 33, pp. 458-471.
- Roy, R., 1949, Decomposition and resynthesis of the micas: *Am. Ceramic Soc. Jour.*, v. 32, pp. 202-209.
- Russell, M. B., and Haddock, J. L., 1940, The identification of the clay minerals in five Iowa soils by the thermal method: *Soil Sci. Soc. America Proc.*, v. 5, pp. 90-94.
- Sabatier, M., 1949, Researches on glauconite: *Soc. franc. Mineral. and Cryst. Bull.*, v. 72, pp. 475-542.
- Sabatier, G., 1950, Effect of the dimensions of chlorite crystals on their differential thermal analysis curves: *Soc. franc. mineral. Bull.*, v. 73, pp. 43-48.
- Satoh, S., 1918, Endo- and exothermic change of the kaolinite in Japan: *Jour. Chem. Ind., Japan*, v. 21, pp. 631-648.
- Satoh, S., 1921, A study of the heating and cooling curves of Japanese kaolinite: *Am. Ceramic Soc. Jour.*, v. 4, pp. 182-194.
- Satoh, S., 1923, Heat effects on fire clays and their mixtures: *Science Repts. Tohoku Imp. Univ.*, ser. 3, v. 1, no. 3, pp. 157-201.
- Saunders, H. L., and Giedroyc, V., 1950, Differential thermal analysis in controlled atmosphere: *British Ceramic Soc. Trans.*, v. 49, pp. 365-374.
- Schafer, G. M., and Russel, M. B., 1942, The thermal method as a quantitative measure of clay mineral content: *Soil Sci.*, v. 53, pp. 353-364.
- Schwob, Y., 1949, The simple and complex rhombohedral carbonates of calcium, magnesium, and iron; Their thermal dissociation: *Rev. materiaux construction trav. publ.*, Edit. C, no. 411, pp. 409-420.
- Schwob, Y., 1950, I. Simple and complex rhombohedral carbonates of calcium, magnesium, and iron; Their thermal dissociation: *Rev. materiaux construction trav. publ.*, Edit. C, no. 413, pp. 33-43, 85-90.
- Schwob, Y., 1950a, II. Simple and complex rhombohedral carbonates of calcium, magnesium, and iron; Their thermal dissociation: *Rev. materiaux construction trav. publ.*, Edit. C, no. 415, pp. 128-133.
- Sedletskii, I. D., 1949, X-ray characteristics of the mineral "monothermite": *Doklady Akad. Napk. (USSR)*, v. 67, pp. 353-355.
- Sedletskii, I. D., 1949, Mineralogy of white clays of the Rostov region: *Doklady Akad. Nauk. (USSR)*, v. 69, pp. 69-72.
- Sedletskii, I. D., and Samodurov, P. S., 1949, Magnesium monothermite: *Zapiski Vsesoyuz. Mineral. Obshechestva.*, v. 78, pp. 274-276.
- Shorter, A. J., 1948, Contribution to the theory of differential thermal analysis; I. Measurement of the heat required in firing clays: *British Ceramic Soc. Trans.*, v. 47, p. 22.
- Siefert, A. C., and Henry, E. C., 1947, Effect of exchangeable cations on hydrophilic nature of kaolin and bentonite: *Am. Ceramic Soc. Jour.*, v. 31, pp. 37-38.

- Smothers, W. J., and Dziemianowicz, T., 1951, Refractory and thermal observations on an Arkansas clay deposit: *Am. Ceramic Soc. Bull.*, v. 30, pp. 74-75.
- Smothers, W. J., Chiang, Yao, and Wilson, A., 1951, Bibliography of differential thermal analysis: *Univ. Arkansas Inst. of Science and Tech., Research ser.*, no. 21, 44 pp.
- Smothers, W. J., and Chiang, Yao, 1952, Differential thermal curves of selected lignites: *Econ. Geology*, v. 47, pp. 384-397.
- Smyth, H. T., 1951, Temperature distribution during mineral inversion and its significance in differential thermal analysis: *Am. Ceramic Soc. Jour.*, v. 34, pp. 221-224.
- Soveri, U., 1949, Differential thermal analysis as an aid to the investigation of our (Finnish) clays: *Geologi*, v. 1, pp. 9-10.
- Soveri, U., 1950, Differential thermal analysis of some Quaternary clays of Fennoscandia: *Ann. Acad. Scient. Fennicae, A. III*, v. 23, 103 pp.
- Speil, S., 1944, Application of thermal analysis to clays and aluminous minerals: *U. S. Bur. Mines, Rept. Inv.* 3764, 36 pp.
- Speil, S., Berkelhamer, L. H., Pask, J. A., and Davies, B., 1945, Differential thermal analysis: Its application to clays and other aluminous minerals: *U. S. Bur. Mines, Tech. Paper* 664, 81 pp.
- Splichal, J., Skramovsky, S., and Goll, J., 1936, Thermal decomposition of carbonate minerals: *Veda prirodni*, v. 17, pp. 206-213.
- Stone, R. L., 1951, Differential thermal analysis under controlled thermodynamic conditions: *Ohio State Univ. Engineering Experiment Sta. Bull.*, no. 149.
- Stone, R. L., 1952, Apparatus for differential thermal analysis under controlled partial pressure of H₂O, CO₂ or other gases: *Am. Ceramic Soc. Jour.*, v. 35 (3), pp. 76-82.
- Stone, R. L., 1952, Differential thermal analysis of kaolin group minerals under controlled partial pressure of H₂O: *Am. Ceramic Soc. Jour.*, v. 35 (4), pp. 90-99.
- Tereschenko, A. V., and Dudarskii, I. E., 1935, Regulating the plastic properties of clay: *Ogneuporui*, v. 3, pp. 127-134, 208-216, 298-304.
- Theron, J. J., Heydrenrych, J. C., and Anderson, F., 1949, A thermocouple microvoltmeter for use in the differential thermal analysis of clays: *Jour. Sci. Inst.*, v. 26, p. 233.
- Thilo, E., and Schunemann, H., 1937, Chemical studies of silicates; IV. Behavior of pyrophyllites Al₂(Si₄O₁₀)(OH)₂ on heating and the existence of a "water-free" pyrophyllite, Al₂(Si₄O₁₀)O: *Zeitschr. anorg. allgem. Chem.*, v. 230, pp. 321-335.
- Trombe, F., 1938, Estimation of quartz by differential thermal analysis: *Acad. Sci. Paris, Comptes rendus*, v. 207, pp. 1111-1113.
- Vakhrushev, V. A., 1949, On the ferrihalloysite from the Anatolsky silicate-nickel ore deposits in the middle Urals: *Soc. Russe Min. Mem.*, v. 78, pp. 272-274.
- Vasenin, F. I., 1937, Thermal analysis of silicates: *Vsesoyuz. Nauch.-Issledovatel'. Inst. Tsement., Byull.*, 1937, No. 1, pp. 79-83.
- Vold, M. J., 1949, Differential thermal analysis: *Anal. Chem.*, v. 21, pp. 683-688.
- Vold, M. J., Hattiangdi, G. S., and Vold, R. D., 1949, Phase state and thermal transitions of greases: *Ind. Eng. Chem.*, v. 41, pp. 2539-2546.
- Vold, M. J., and Vold, R. D., 1950, The phase behavior of lithium stearate in cetane and in decalin: *Jour. Colloid Sci.*, v. 5, pp. 1-19.
- Vold, R. D., 1941, Anhydrous sodium soaps; Heats of transition and classification of the phases: *Am. Chem. Soc. Jour.*, v. 63, pp. 2915-2924.
- Vold, R. D., and Vold, M. J., 1945, Thermal transitions of the alkali palmitates: *Jour. Phys. Chemistry*, v. 49, p. 32.
- Vold, R. D., 1945, The polymorphism and transitions of anhydrous sodium stearate: *Jour. Phys. Chemistry*, v. 49, pp. 315-328.
- Vold, R. D., 1947, Phase boundaries in concentrated systems of sodium oleate and water: *Jour. Phys. Colloid Chem.*, v. 51, pp. 797-815.
- Vold, R. D., Grandine, J. D., and Vold, M. J., 1948, Polymorphic transformations of calcium stearate monohydrate: *Jour. Colloid Sci.*, v. 3, p. 3399.
- Wallach, R., 1913, Thermal analysis of clays: *Acad. Sci. Paris Comptes rendus*, v. 157, pp. 48-50.
- Warde, J. M., and Denyschen, J. H., 1949, Differential thermal analysis of some South African fire clays and other ceramic materials: *Geol. Soc. South Africa, Trans.*, v. 52, pp. 413-431.
- Warde, J. M., 1950, Refractory clays in the Union of South Africa: *Am. Ceramic Soc. Bull.*, v. 29, pp. 257-260.
- Whitehead, W. L., and Breger, I. A., 1950, Vacuum differential thermal analysis: *Science*, (new ser.), v. 111, pp. 279-281.
- Wiklander, L., 1950, Differential thermal analysis of some Quaternary clays of Sweden: *Geol. Foren. i Stockholm Forh.*, v. 72, pp. 119-132; English summary: *Nature*, v. 166, pp. 276-277.
- Wilcox, R. L., and Bollard, J. R., 1936, A self-recording apparatus for thermal analysis: *Metal and Alloys*, v. 7, pp. 221-224.
- Wittels, M., 1951, The differential thermal analyzer as a micro-calorimeter: *Am. Mineralogist*, v. 36, pp. 615-622.
- Wittels, M., 1951, Some aspects of mineral calorimetry: *Am. Mineralogist*, v. 36, pp. 760-767.
- Wittels, M., 1951, Structural transformations in amphiboles at elevated temperatures: *Am. Mineralogist*, v. 36, pp. 851-859.
- Wittels, M., 1952, The structural disintegration of some amphiboles: *Am. Mineralogist*, v. 37, pp. 28-37.
- Wohlen, R., 1913, Thermal analyses of clays, bauxites and some allied materials: *Sprechsaal*, v. 46, pp. 719-721, 733-735, 749-751, 767-769, 781-783.
- Yamauchi, T., and Suzuki, S., 1942, Thermal analysis of Japanese raw clays: *Japan Ceramic Assoc. Jour.*, v. 51, pp. 211-221.
- Zakharov, M. V., 1940, Establishing optimum conditions for heating and cooling during differential thermal analysis: *Zavodskaya Lab.*, v. 8, pp. 968-973, 1939. . . . *Khim. Referat. Zhur.*, no. 3, p. 50, 1940.
- Zhuravlev, V. F., and Zhitomirskaya, V. I., 1950, Binding properties of crystal hydrates of the sulfate type: *Jour. Applied Chemistry (USSR)*, v. 23, pp. 113-117.
- Zhuravlev, V. F., and Zhitomirskaya, V. I., 1950, Binding properties of crystal hydrates of the sulfate type: *Jour. Applied Chemistry (USSR)*, v. 23, pp. 230-232.